

Serial No.: 10/722,830
Art Unit: 1732

Listing of Claims:

Claim 1. (Currently amended) A method of shaping a flexible dental product selected from the group consisting of nightguards and splints, comprising the steps of:

shaping a light curable polymerizable composition into of a dental product in a mouth of a patient,

irradiating the polymerizable composition with light to partially cure the composition,

removing the dental product from the mouth of the patient,

irradiating said light curable polymerizable composition being adapted with light to form a cured flexible dental polymeric material product, said polymeric material product having a flexural modulus of less than 250,000 psi and a flexural strength of less than 7,000 psi at 37°C.

Claim 2. (Canceled)

Claim 3. (Original) The method of claim 1 wherein a first portion of said light curable polymerizable composition is at least partially cured in a mouth of a patient and a second portion of said light curable polymerizable composition is at least partially cured in a light curing apparatus.

Claim 4. (Original) The method of claim 1 wherein said light curable polymerizable composition effectively requires application of more than 0.001 psi of pressure to said composition to force said composition to flow, and said composition is moldable by a pressure of at least 1 psi.

Serial No.: 10/722,830
Art Unit: 1732

RECEIVED
CENTRAL FAX CENTER

NOV 14 2007

Claim 5. (Canceled)

Claim 6. (Currently amended) The method of claim 1 wherein said flexural modulus of said polymeric material ~~product~~ and said flexural strength of said polymeric ~~material~~ product are at least 20 percent less at 37°C. than at 23°C.

Claim 7. (Currently amended) The method of claim 1 wherein said flexural modulus of said polymeric material ~~product~~ and said flexural strength of said polymeric material ~~product~~ are at least 50 percent less at 37°C. than at 23°C.

Claim 8. (Currently amended) The method of claim 1 wherein said flexural modulus of said polymeric material product and said flexural strength of said polymeric material product are at least 70 percent less at 37°C. than at 23°C.

Claim 9. (Currently amended) The method of claim 1 wherein said polymeric material ~~product~~ has a flexural modulus at 37°C. of less than 100,000 psi and a flexural strength at 37°C. of less than 5,000 psi.

Claim 10. (Currently amended) The method of claim 1 wherein said polymeric material ~~product~~ at 37°C. has a flexural modulus of less than 60,000 psi and a flexural strength of less than 3,000 psi.

Serial No.: 10/722,830
Art Unit: 1732

Claim 11. (Currently amended) The method of claim 1 wherein said polymeric material product at 37°C. has a flexural modulus of less than 40,000 psi and a flexural strength of less than 2,000 psi.

Claim 12. (Currently amended) The method of claim 1 wherein said polymeric material product has a compliance of at least 1×10^{-5} in²/pound.

Claim 13. (Currently amended) A method of shaping a flexible dental product selected from the group consisting of nightguards and splints, comprising the steps of:

shaping a light curable polymerizable composition to form a dental product over a cast model of a patient's teeth,

light curing irradiating said light curable polymerizable composition being adapted to form a cured flexible dental polymeric material product, said product having a flexural modulus of less than 250,000 psi and a flexural strength of less than 9,000 psi at 23°C,

removing the flexible dental product from the cast model.

Claim 14. (Currently amended) The method of claim 13 wherein said flexural modulus of said polymeric material product and said flexural strength of said polymeric material product are at least 70 percent less at 37°C. than at 23°C.

Serial No.: 10/722,830

Art Unit: 1732

Claim 15. (Currently amended) The method of claim 13 wherein said polymeric material product at 37°C. has a flexural modulus of less than 100,000 psi and a flexural strength of less than 3,000 psi.

Claim 16. (Currently amended) The method of claim 13 wherein said polymeric material product at 37°C. has a flexural modulus of less than 80,000 psi and a flexural strength of less than 2,000 psi.

Claims 17-24. (Canceled)

Claim 25. (New) The method of claim 13, wherein said flexural modulus of said polymeric product and said flexural strength of said polymeric product are at least 20 percent less at 37 °C than at 23 °C.

Claim 26. (New) The method of claim 13, wherein said flexural modulus of said polymeric product and said flexural strength of said polymeric product are at least 50 percent less at 37 °C than at 23 °C.